OXIME SILANE

Andisil® MT 9010

CAS# n/a



TYPICAL PROPERTIES*

| CHEMICAL NAME | Blend of MOS [Methyl tris(MEKO)silane] & TOS [Tetrakis(MEKO)silane] |
|-----------------------|---|
| APPEARANCE | Colorless to brownish transparent liquid |
| MOS / TOS CONTENT | MOS: 83-88 TOS: 8.0-9.5 |
| MEKO CONTENT | 1.5% Max |
| BOILING POINT °C/mmHg | 330 °C [760 mmHg] |
| REFRACTIVE INDEX | 1.455 +/- 0.0020 |
| рН | 6.5 -7 .5 |

^{*} These properties are not intended to be used as specifications but only as suggested characteristics

DESCRIPTION

- Used as a crosslinker in RTV silicone rubber and neautral silcione sealants
- Can improve hardness, has short tack-free time and full curing time for silicone sealant due to the tetra functional group

STORAGE & SHELF LIFE

When stored at or below 25°C (77°F) in the original unopened containers, this product has a minimum shelf life of one (1) year.

PACKAGING

Packaging options are available upon request.

For additional information on the product, please contact your Sales Representative.



We believe that the information shown in this Product Bulletin to be an accurate description of the typical characteristics and/or uses of the product. Any suggestions of uses are not to be taken as an inducement to infringe any particular domestic or foreign patent. We recommend that the product be thoroughly tested for a specific application to determine the performance, efficacy and its safe handling and use.