

SILSOURCE™ SDF-350FGK

POLYDIMETHYLSILOXANE 350 cSt FOOD GRADE KOSHER

PRODUCT DESCRIPTION

Polydimethylsiloxane 350 cSt Food Grade Kosher is a silicone Fluids that complies with food safety and Kosher certification standards. It is widely used in applications requiring food-grade compliance, ensuring purity, safety, and adherence to Kosher dietary regulations.

TYPICAL PRODUCT DATA*

Property	Unit	Typical Value
CAS#	-	63148-62-9
Viscosity	cSt	350
Formula	-	(C ₂ H ₆ OSi) _n
Appearance	-	Colorless clear liquid
Purity	%	>99%
Flash Point	°C	>270
Surface Tension	mN/m	21
Density	g/cm ³	0.970
Refractive Index	-	1.403

* These values are not intended to be used as specifications but as suggested characteristics

PACKAGING

The size of the available packages can be checked with Sales Department. Silicone Fluid is typically supplied in 200kg steel drums and 1000kg IBC totes.

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEET AND CONTAINER LABELS FOR SAFE USE, PHYSICAL, ENVIRONMENTAL, AND HEALTH HAZARD INFORMATION.


LIMITATIONS: Not intended for human injection. This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Limited Warranty: Silsource Inc. warrants to Buyer that for a period of 12 months from the date of manufacture of the products, such products will materially conform to Silsource Inc.'s specifications in effect as of the date of manufacture. This warranty does not apply where the products have (a) been subjected to abuse, misuse, neglect, negligence, accident, improper testing, improper installation, improper storage, improper handling, abnormal physical stress, abnormal environmental conditions, or use contrary to any instructions issued by Silsource Inc.; (b) been reconstructed, repaired, or altered by persons other than Silsource Inc. or its authorized representatives; or (c) been used with any third-party product or hardware that has not been previously approved in writing by Silsource Inc. Buyer's exclusive remedy for breach of the limited warranty shall be a refund of the purchase price or replacement of the product, at Silsource Inc.'s sole discretion.

Disclaimer: EXCEPT FOR THE EXPRESS LIMITED WARRANTY SET OUT ABOVE, SILSOURCE INC. MAKES NO WARRANTY WHATSOEVER WITH RESPECT TO THE GOODS, INCLUDING ANY (A) WARRANTY OR CONDITION OF MERCHANTABILITY; (B) WARRANTY OR CONDITION OF FITNESS FOR A PARTICULAR PURPOSE; (C) WARRANTY OR CONDITION OF TITLE; OR (D) WARRANTY AGAINST INFRINGEMENT OF INTELLECTUAL PROPERTY RIGHTS OF A THIRD PARTY, WHETHER EXPRESS OR IMPLIED AND WHETHER ARISING BY LAW, COURSE OF DEALING, COURSE OF PERFORMANCE, USAGE OF TRADE, OR OTHERWISE. BUYER ACKNOWLEDGES THAT IT HAS NOT RELIED UPON ANY REPRESENTATION, CONDITION, OR WARRANTY MADE BY SILSOURCE INC., OR ANY OTHER PERSON ON SILSOURCE INC.'S BEHALF, EXCEPT AS SPECIFICALLY PROVIDED ABOVE.

VERSION: 1 Last updated: 24 April 2024

TECHNICAL DATA SHEET



TYPICAL FEATURES AND APPLICATIONS

SDF-350FGK are a series of silicone fluids with various viscosities and of excellent purity. They are chemically known as dimethyl polysiloxane and useful due to their thermal stability or resistance to change with changes in temperature. The fluids are completely soluble in all viscosities of dimethyl polysiloxane fluids and are heat stable and resistant to oxidation. They are inert, non-corrosive, nontoxic, clear and colorless.

INFORMATION FOR USE

Silicone fluids are useful due to their thermal stability or resistance to change with changes in temperature. The fluids are completely soluble in all viscosities of dimethyl polysiloxane fluids and are heat stable and resistant to oxidation. They are inert, noncorrosive, nontoxic, clear and colorless. It widely used in various industrial and consumer applications requiring a balance of spreadability and viscosity.

SHELF LIFE AND STORAGE

The shelf life, when the container is stored unopened and under proper conditions (ambient temperatures or below 50°), is expected to be three years from the date of manufacture.